

Resinfam Product Selection Guide



Sales Dept
 +9821-88775311
 +9821-88885376

	Chemical Composition	Plasticizer	Solids Content (%)	pH Value	MFFT (°C)	Viscosity (cP)	Interior Paints	Exterior Paints	Gloss Paints	Wood Paints	Textured Coatings	Primers	Silicate Systems	Silicone Coatings	Crack Bridging Coatings	Flexible Coatings	Tile Adhesive	Plasters	Carpet Back Coatings	Woven Carpet Back Coating	Pigment Printing	Non-woven Finishing	Wood Adhesive	Paper and Packaging Adhesive	Book Binding	Veneering	Cellophane Adhesive	Dispersing Agent	Thickener		
Polyfam 101	Sodium Salt of a Polyacrylate	-	28 ± 2	9-11	NA	125-325																								●	
Polyfam 103	Acrylic Copolymer	-	28 ± 0.5	2.5-3.5	NA	Max 15																								●	
Polyfam 300	Vinyl Acetate	-	50 ± 1	3-5	+14	70000-100000	○												●			●	●	○							
Polyfam 301	Vinyl Acetate	-	50 ± 1	3-5	+14	100000-140000											○		●			●	●	○							
Polyfam 302	Vinyl Acetate	-	50 ± 1	3-5	+14	1500 - 4500													●												
Polyfam 320	Vinyl Acetate	+	50 ± 1	3-5	+2	60000-90000														●			○	●	●						
Polyfam 321	Vinyl Acetate	+	49 ± 1	3-5	+2	50000-80000																	○	●	●						
Polyfam 324	Vinyl Acetate	+	50 ± 1	4-5	+2	20000-50000														●					●						
Polyfam 330	Vinyl Acetate	+	37 ± 1	4-5	+5	30000-50000														●											
Polyfam 350	Vinyl Acetate	+	50 ± 1	3-5	-2	75000-125000																		●	●						
Polyfam 360	Vinyl Acetate	-	50 ± 1	5-6	+16	90000-130000																		●	●						
Polyfam 365	Vinyl Acetate	-	50 ± 1	3-5	+15	120000-180000											○							●	●						
Polyfam 395	Vinyl Acetate	-	20 ± 1	5-7	-1	3500-5500	●				●																				
Polyfam PR501	Vinyl Acetate	-	46 ± 1	3-4	+16	25000-35000																		●	○		●				
Polyfam 420	Vinyl Acetate/Acrylic/VeoVa	-	50 ± 1	4-5	-1	7000-12000	●	●			○																				
Polyfam 425	Vinyl Acetate/Acrylic	-	52 ± 1	4-5	-2	2000-4000	●	○			●					●															
Polyfam 430	Vinyl Acetate/Acrylic	-	50 ± 1	4-5	0	2000-4000	●	○				○																			
Polyfam 431	Vinyl Acetate/Acrylic	-	55 ± 1	4-5	0	3000-5000	●	●																							
Polyfam 450	Vinyl Acetate/Acrylic	-	50 ± 1	4-5	+10	7000-15000																				●					
Polyfam 5150	Vinyl Acetate/Acrylic	-	55 ± 1	4-6	+6.5	4000-7000	●	○									●														
Polyfam MTB	Vinyl Acetate/Acrylic	-	40 ± 1	6.3-6.5	< -5	30-60																●									
Polyfam 706	Self Crosslinking Pure Acrylic	-	46 ± 1	2-3	+20	50-350																	●								
Polyfam 707	Styrene/Acrylic	-	50 ± 1	7-9	+18	2400-4600	●	●	○	○	●	●	●	●																	
Polyfam 735	Styrene/Acrylic	-	50 ± 1	7.5-8.5	+15	2400-4600	●	●			●	●	●	●		○	●	●													
Polyfam 736	Styrene/Acrylic	-	50 ± 1	7.5-8.5	+17	2400-4600	●	●			●	●	●	●		○	●	●													
Polyfam 765	Styrene/Acrylic	-	50 ± 1	7.5-8.5	0	2400-4600	●	●			●	●	●	●	●	○	●	●									○				
Polyfam 766	Styrene/Acrylic	-	50 ± 1	7.5-8.5	0	2400-4600	●	●			●	●	●	●	●	○	●	●													
Polyfam 774	Pure Acrylic	-	50 ± 1	8.5-10.5	17.5	150-250	●	●	●	●	○	●																			
Polyfam 777	Pure Acrylic	-	46 ± 1	8-9	+15	50-150	●	●	●	●	○	●															○				

● Main application ○ Other applications